

SPECIFICATION

Electronic Version 1.2.8

Stylesheet Version 1.0

BIMODAL CATALYST-UREA SCR SYSTEM FOR ENHANCED NO_x CONVERSION AND DURABILITY

Background of Invention

[0001] 1. Field of the Invention

[0002] The present invention relates to methods of and systems for reducing NO_x emissions from the exhaust of an internal combustion engine and, in particular, to methods of reducing NO_x emission by adjusting the NO to NO₂ ratio in the exhaust before the exhaust gases flow through an SCR catalyst.

[0003] 2. Background Art

[0004] Emissions of NO_x and particulate matter (PM) are of primary concern for both diesel and gasoline vehicles to meet future emissions standards. Diesel vehicles have significant advantages over their gasoline counterparts including a more efficient engine, higher fuel economy, and lower emissions of HC, CO, and CO₂. For example, diesel vehicles potentially have a 40% higher fuel economy than current gasoline vehicles with 20% lower CO₂ emissions.

[0005] Control of NO_x onboard a diesel vehicle is not a trivial task due to the high oxygen content of the exhaust gas. Such high oxygen fuel systems are typically referred to as lean burn systems. In such lean burn systems, NO_x control is more difficult because of the high O₂ concentration in the exhaust, making conventional three-way catalysts ineffective. The available technologies for NO_x reduction in lean environments include Selective Catalytic Reduction (SCR), in which NO_x is continuously removed through active injection of a reductant over a catalyst and Lean

[0007] $4 \text{NH}_3 + 4 \text{NO} + \text{O}_2 \rightarrow 4 \text{N}_2 + 6 \text{H}_2\text{O}$

[0009] $4 \text{NH}_3 + 2 \text{NO} + 2 \text{NO}_2 \rightarrow 4 \text{N}_2 + 6 \text{H}_2\text{O}$

[0011] Although the increased NO₂ is desirable in a vehicle exhaust, the prior art fails to teach a method for systematically and reliably attaining an optimal NO to NO₂ ratio in the exhaust. Furthermore, the prior art fails to teach a method that can be adjusted to give optimal performance for a given type of automobile engine.

Summary of Invention

[0012] The present invention overcomes the problems encountered in the prior art by providing a method of reducing NO_x in exhaust gases of an internal combustion engine. The method of the present invention comprising the selective oxidation of the exhaust gases of an engine in which the NO and hydrocarbons in a first portion of the exhaust gases are oxidized separately from the remaining second portion of the exhaust gases. In this second gas portion, only the hydrocarbons are oxidized while the NO is left essentially unreacted. The resulting combined exhaust of the first and second exhaust gas portions optimally have a NO to NO_2 ratio of about 1. As set forth above, this ratio is found to be more efficiently reduced by an SCR catalyst. The present invention provides a systematic approach for adjusting the NO to NO_2 ratio over a wide range of values by varying the amount of gases that comprise the first and second gas portions. Specifically, a first and second exhaust stream from an internal combustion engine are each separately passed through a different catalytic chamber. One exhaust stream is passed through a chamber that oxidizes both hydrocarbons and NO, while the other exhaust stream is passed through a second catalytic chamber that only efficiently oxidizes hydrocarbons while leaving NO essentially unreacted. The two exhaust gas streams are then recombined together and passed through an SCR catalyst. Accordingly, the present invention simultaneously oxidizes hydrocarbons in the exhaust which tend to poison the SCR catalyst and generates a NO to NO_2 ratio of about 1 in which NO_x is more rapidly and efficiently reduced by the SCR catalyst.

[0013] In another embodiment of the present invention, a vehicle exhaust system deploying the method of the present invention is provided. The vehicle exhaust system of the present invention includes two different catalytic regions. One chamber efficiently oxidizes both hydrocarbons and NO, while the other region oxidizes hydrocarbons while leaving NO essentially unreacted. The exhaust system of the present invention further includes an SCR located downstream of the first and second catalytic regions.

Brief Description of Drawings

[0014] Figure 1 is a plot of the NO_x conversion efficiency for a gas sample containing varying amounts of hydrocarbons versus temperature;

- [0015] Figure 2 is a plot of the conversion efficiency for a pure NO stream flowing through the SCR catalyst as a function of temperature after various periods of hydrothermal aging at 670 ° C;
- [0016] Figure 3 is a plot of the conversion efficiency for a gas stream having NO and NO₂ in a ratio of about 1:1 flowing through the SCR catalyst as a function of temperature after various periods of HT aging at 670 ° C;
- [0017] Figure 4 is a plot of the conversion efficiency for the oxidation of NO to NO₂ for a gas stream having 350 ppm NO, 14% O₂, 5% CO, 4.5% H₂O, and balance N₂ flowing over a platinum and a palladium catalyst;
- [0018] Figure 5a is a longitudinal cross-section of monolith which has a plurality of essentially parallel tubes;
- [0019] Figure 5b is a transverse cross-section of monolith which has a plurality of essentially parallel tubes;
- [0020] Figure 6 is a schematic of the method of the present invention utilizing catalytic chambers which are monoliths;
- [0021] Figure 7 provides a longitudinal (cross-section parallel to the flow direction) cross-section through a particulate filter;
- [0022] Figure 8 is a schematic of the method of the present invention utilizing catalytic chambers which are particulate filters;
- [0023] Figure 9 is a transverse cross-section through a monolith illustrating a first and second group of tubes coated with different catalytic materials; and
- [0024] Figure 10 is a schematic of the method of the present invention utilizing a monolith, with a first group of the tubes coated with a first catalytic material that oxidizes the NO and the hydrocarbons, and a second group of the tubes are with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted.

Detailed Description

invention provides a systematic approach for adjusting the NO to NO₂ ratio over a wide range of values by varying the amount of gases that comprise the first and second gas portions. In a typical exhaust from a diesel engine, the ratio of NO to NO₂ is approximately 10 (that is, there is a 10-fold excess of NO). When the ratio of the volume of the first exhaust to the second exhaust is about 1, the exhaust has been separated into two streams of approximately equal volume. Accordingly, this volume ratio results in a recombined exhaust gas that is 50/50 mixture of NO/NO₂. This ratio of NO to NO₂ is more rapidly and efficiently reduced by a urea or ammonia utilizing SCR (Selective Catalytic Reduction) catalyst than either a predominantly NO or NO₂ containing gas stream.

[0034] With reference to Figures 2 and 3, a plot of NO_x conversion efficiency for an SCR catalyst is provided. The catalysts were aged for 16-hour increments up to 48 hours in a 670 ° C gas stream. In Figure 2, the conversion efficiency for a pure NO stream flow through the SCR catalyst as a function of temperature is given at varying times. There is significant loss of activity over the 48-hour aging cycle. Figure 3 shows activity with time reducing a 50:50 stream of NO:NO₂. There is a higher initial conversion and far less deterioration than using NO alone. At temperatures between 200 ° and 400 ° C, the SCR catalyst is observed to experience a significant loss of efficiency over time. However, as illustrated in Figure 2, a NO and NO₂ mixture shows an insignificant decrease in efficiency for the same temperature over the same time period. Accordingly, the method of the present invention provides superior NO_x conversion efficiency over the temperature ranges characteristic for a vehicle exhaust system.

[0035] In an embodiment of the present invention, the step of oxidizing the first exhaust gas portion comprises flowing the first exhaust gas portion through a first catalytic chamber that includes platinum and the step of oxidizing the second exhaust gas comprises flowing the second gas portion through a second catalytic chamber that includes palladium. Both platinum and palladium are known to oxidize hydrocarbons. However, platinum is found to efficiently oxidize NO to NO₂, while palladium does not. With reference to Figure 4, a plot of the conversion efficiency for the oxidation of NO to NO₂ for a gas stream having 350 ppm NO, 14% O₂, 5% CO, 4.5% H₂O, and balance N₂ flowing over a platinum and a palladium catalyst is provided. Figure 4

clearly demonstrates the effectiveness of platinum and the minimal ability of palladium to oxidize NO.

[0036] Preferably, this first catalytic chamber is a monolith, the monolith comprising a plurality of essentially parallel tubes through which the exhaust gases flow. Furthermore, the essentially parallel tubes are coated with platinum. The construction of the monolith is best understood by reference to Figures 5a and 5b. Figure 5a provides a longitudinal cross-section of monolith 5 which has a plurality of essentially parallel tubes 10. Figure 5b is a top view of the monolith illustrating that the plurality of tubes 10 form a honeycomb arrangement. Furthermore, this embodiment is best understood by reference to Figure 6 which provides a schematic of the method of the present invention utilizing catalytic chambers which are monoliths. In Figure 6, an exhaust gas stream has been divided into gas streams 15, 20. Gas stream 20 flows through first catalytic monolith 30 which is coated with platinum, and gas stream 15 flows through catalytic monolith 25 which is coated with palladium. Gas streams 15 and 20 are then recombined at joint 40 to form recombined gas stream 45. Recombined gas stream 45 then flows through SCR catalyst 50 where the NO and NO₂ are reduced. The reductant is injected into the exhaust gas stream at position 52.

[0037] In a variation of this embodiment, the first and second catalytic chambers are each individually a particulate filter having channels through which the exhaust gases flow. In the case of the first catalytic chamber, the channels are coated with platinum. For the second catalytic chamber, the channels are coated with palladium. Particulate filters differ from the monoliths described above in that the channels of a particulate chamber are blocked off on one end, thereby causing gases that enter to diffuse to adjacent channels before emerging from the opposite ends of the filter. Accordingly, particulate matter is removed from the gas stream. The construction of the particulate filter is best understood by reference to Figure 7. Figure 7 provides a longitudinal (cross-section parallel to the flow direction) cross-section through particulate filter 53. Channel 55 is blocked off on end 60, and channel 65 is blocked off on end 70. Accordingly, gas that enters end 75 of channel 55 cannot emerge from end 65. Instead, the gas must flow through a wall, such as wall 80, and flow through an adjacent channel, such as channel 65, where it can emerge from end 90 which is not blocked off. The method of this variation is best understood with reference to Figure

8. In Figure 8, an exhaust gas stream has been divided into gas streams 95, 100. Gas stream 100 flows through first particulate filter 110 which is coated with platinum, and gas stream 95 flows through second particulate filter 105 which is coated with palladium. Gas streams 95 and 100 are then recombined at joint 115 to form recombined gas stream 120. Recombined gas stream 120 then flows through SCR catalyst 125 where the NO and NO₂ are reduced. The reductant is injected into the exhaust stream at position 127.

[0038]

In yet another embodiment of the present invention, a method of reducing NO_x in exhaust gases of an internal combustion engine is provided. The method of this embodiment corresponds to combining steps a, b, and c as set forth above. The combination of these steps is accomplished by flowing the exhaust gases through a single catalytic monolith where the catalytic monolith comprises a plurality of essentially parallel tubes through which the exhaust gases flow. However, in this embodiment, a first group of the tubes are coated with a first catalytic material that oxidizes the NO and the hydrocarbons, and a second group of the tubes are coated with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted. Preferably, the first group of tubes is coated with a first coating that includes platinum, and the second group of tubes is coated with a second coating that includes palladium. The ratio of the number of tubes in the first group of tubes to the number of tubes in the second group of tubes is from about 0.5 to about 2. More preferably, the ratio of the number of tubes in the first group of tubes to the number of tubes in the second group of tubes is about 1. This embodiment is best understood by reference to Figure 9, which provides a schematic of the method of the present invention a first group of the tubes are coated with a first catalytic material that oxidizes the NO and the hydrocarbons and a second group of the tubes are coated with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted. Figures 9a, 9b, and 9c provide a transverse cross-section through monolith 130. The interior walls of the tubes 135 in monolith section 140 are coated with a first catalytic material that oxidizes the NO and the hydrocarbons, while the interior walls of the tubes 142 in monolith section 145 are coated with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted. The only differences between Figures 9a, 9b and 9c are the different

cross-sectional shapes between Figure 9a and Figures 9b and 9c and the choice of which section of tubes to coat with the different catalysts in Figure 9b and Figure 9c.

[0039] With reference to Figure 10, a schematic of the method utilizing a monolith with a first group of the tubes coated with a first catalytic material that oxidizes the NO and the hydrocarbons and a second group of the tubes are with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted is provided. In Figure 10, gas stream 150 flows through catalytic monolith 155 in which first group of the tubes 160 are coated with a first catalytic material that oxidizes the NO, and the hydrocarbons and second group of the tubes 165 are coated with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted. Treated gas stream 170 then flows through SCR catalyst 175 where the NO and NO₂ are reduced. The reductant is injected into the exhaust stream at position 180. In a variation of this embodiment, catalytic monolith 155 is replaced by a particulate filter. In this variation, first groups of tubes 160 and second group of tubes 165 will be the channels of a particulate filter as described above for Figure 7.

[0040] In yet another embodiment of the present invention, a vehicle exhaust system which reduces NO_x in the exhaust gases of an internal combustion engine is provided. This vehicle exhaust system comprises:

[0041] a first catalytic chamber through which a first exhaust gas portion flows wherein the first catalytic chamber oxidizes NO and hydrocarbons; and

[0042] a second catalytic chamber through which a second exhaust gas portion flows wherein the second catalytic chamber oxidizes hydrocarbons while leaving NO essentially unreacted.

[0043] The vehicle exhaust system of this embodiment further comprises an SCR catalyst located downstream of the first and second catalytic chambers. Preferably, the first and second catalytic chambers are each separately and individually a monolith having a plurality of essentially parallel tubes through which the exhaust gases flow. The parallel tubes for the first catalytic chamber are coated with platinum, while the parallel tubes for the second monolith are coated with palladium. This embodiment is best understood with reference to Figures 5a, 5b and 6 as described above. In a

variation, the first and second catalytic chambers are each separately and individually a particulate filter having channels through which the exhaust gases flow. This variation is best understood by reference to Figures 7 and 8 as described above. Similarly, the channels for the first particulate filter are coated with platinum, while the channels for the second monolith are coated with palladium. The first exhaust gas portion and second gas portions may be formed by attaching a flow channel from separate sections of the exhaust manifold. Alternatively, a flow divider may be used to separate the first and second exhaust gas portions. Such a flow divider may be any device that separates the flow of the exhaust gas into two gas streams. Such devices include, but are not limited to, a Y or T joint.

[0044] In still another embodiment of the present invention, a variation of the above vehicle exhaust system is provided. This embodiment is best understood with reference to Figures 9 and 10 as described above. The vehicle exhaust system of this variation comprises a catalytic monolith that has a plurality of channels through which the exhaust gases flow, wherein a first group of channels are coated with a first catalytic material that oxidizes the NO and the hydrocarbons, and a second group of the channels are coated with a second catalytic material that oxidizes the hydrocarbons while leaving the NO essentially unreacted. This selective oxidation is accomplished by coating the first group of tubes with a first coating that includes platinum and the second group of tubes is coated with a second coating that includes palladium. In this preferred embodiment, the ratio of the number of tubes in the first group of tubes to the number of tubes in the second group of tubes is preferably from about 0.5 to about 2, more preferably 0.75 to 1.25, and most preferably about 1. In one variation of this embodiment, the first and second groups of channels are different groups of essentially parallel tubes of a monolith as described above by Figures 5 and 9. In another variation of this embodiment, the first and second channels are different groups of channels of a particulate filter as described above for Figure 7.

[0045] While embodiments of the invention have been illustrated and described, it is not intended that these embodiments illustrate and describe all possible forms of the invention. Rather, the words used in the specification are words of description rather than limitation, and it is understood that various changes may be made without

departing from the spirit and scope of the invention.